

ACQPA SYSTEMS JOTUN 2023

Corrosivity CI	NB/M	Sub.	Systems	DFT µm	
C3 H ANV 1389	NB	Steel	Barrier80	40	240
			Penguard Express	140	
			Hardtop XP	60	
C3 H AMV 1389	M	Steel	Barrier80	40	240
			Penguard Express	140	
			Hardtop XP	60	
C3 H AMV 1293	M	Steel	Jotamastic 80	180	240
			Hardtop XP	60	
C3 H AMV 1388	M	Steel	Jotamastic 80 alu	160	240
			Hardtop Flexi	80	
C3 H ANV 1437	NB	Steel	Jotamastic 90 alu	180	240
			Hardtop XP	60	
C3 H AMV 1437	M	Steel	Jotamastic 90 alu	180	240
			Hardtop XP	60	
C4 H AMV 1436	M	Steel	Jotamastic 90 alu	220	280
			Hardtop XP	60	
C4 H ANV 1436 C3 VH ANV 1436	NB	Steel	Jotamastic 90 alu	220	280
			Hardtop XP	60	
C4 H ANV 1522 C3VH ANV 1522	NB	Steel	Jotamastic 90 alu red t	110	280
			Jotamastic 90 alu	110	
			Hardtop XP	60	
C4 H ANV 1390 C3VH ANV 1390	NB	Steel	Barrier 80	40	280
			Penguard Express	180	
			Hardtop XP	60	
C4 H AMV 1390	M	Steel	Barrier 80	40	280
			Penguard Express	180	
			Hardtop XP	60	
C5 H ANV1405 C4VH ANV A405	NB	Steel	Barrier plus	60	280
			Penguard Express	160	
			Hardtop XP	60	
C5 VH ANV1564	NB	Steel	Barrier plus	60	320
			Penguard Express	200	
			Hardtop XP	60	
CX H ANV601 IM4 H ANV601	NB	Steel	Baltoflake		800
IM2 H ANI 1208	NB	Steel	Baltoflake		800
IM2 H ANI 1527	NB	Steel	Marathon 550	200	450
			Marathon 550	250	

H Haute durabilité (15 - 25 ans)
VH Très haute durabilité (> 25 ans)

NB New Building (ouvrages neufs)
M Maintenance